Abrasive Cutter Consumables

Abrasive Blades

Buehler's Abrasive Blades are designed to provide high quality sectioning results with no burning and minimal surface deformation. This can reduce the amount of grinding & polishing required later in the preparation process.

Efficient Cutting with Extended Life

An abrasive blade wears down during cutting to expose new abrasive particles and maintain efficient cutting. However, too fast of a wear rate leads to shortened blade life. Buehler's blades have been designed to balance this wear rate to maintain efficient cutting while extending blade life.

Resin Bond vs Rubber Bond

Buehler's line of abrasive blades includes both rubber bonded and resin bonded blades. While both provide high quality cutting, there are some differences between them. Rubber bonded blades may be thinner for some applications, but emit a burnt rubber odor while cutting. Resin bonded blades offer similar performance with a reduced odor.

Abrasive Blades Selection, 1.25in [32mm] Arbor (Qty 10)

[Blade Thickness is listed under Part Number] ***Rubber Bond*** **= •** ***Resin Bond*** **= ***

Recommended Use	9in [230mm] Chop/Linear	10in [254mm] Chop/Linear	12in [305mm] Chop/Linear	12in [305mm] Orbital
Superalloys, General Steel, Non-Ferrous		12-4205-010• 0.055in [1.4mm]	12-4405-010• 0.055in [1.4mm]	12-4405-010• 0.055in [1.4mm]
Ferrous materials >HRC60	10-4110-010• 0.07in [1.8mm] 102309P* 0.06in [1.5mm]	10-4210-010• 0.07in [1.8mm] 102509P* 0.06in [1.5mm]	12-4110-010• 0.105in [2.7mm] 103009P* 0.079in [2mm]	12-4410-010• 0.105in [2.7mm]
Ferrous materials HRC50-60	10-4112-010• 0.07in [1.8mm] 102310P* 0.06in [1.5mm]	10-4212-010• 0.07in [1.8mm]	10-4412-010• 0.105in [2.7mm] 95B2302* 0.08in [2mm]	12-4410-010• 0.105in [2.7mm]
Ferrous materials HRC35-50	10-4116-010• 0.07in [1.8mm]	10-4216-010• 0.07in [1.8mm] 102510P* 0.06in [1.5mm]	12-4116-010• 0.105in [2.7mm] 103010P* 0.079in [2mm]	12-4416-010• 0.105in [2.7mm]
Ferrous materials HRC15-35	10-4120-010• 0.07in [1.8mm]	10-4220-010• 0.063in [1.6mm] 102511P* 0.06in [1.5mm]	12-4120-010• 0.105in [2.7mm] 103011P* 0.079in [2mm]	12-4420-010• 0.105in [2.7mm]
High Speed Steel, Stainless Steel, Carburized Steel	102308P* 0.06in [1.5mm]	102508P* 0.06in [1.5mm]	103008P* 0.079in [2mm]	
Delicate Cutting	10-4127-010• 0.032in [0.8mm]	10-4227-010• 0.032in [0.8mm]		
Titanium Alloys, Zirconium Alloys, Ductile Materials	10-4145-010• 0.063in [1.6mm] 102307P* 0.06in [1.5mm]	10-4245-010• 0.063in [1.6mm] 102507P* 0.06in [1.5mm]	12-4145-010• 0.055in [1.4mm] 103007P* 0.079in [2mm]	
Non-Ferrous Materials (Aluminum, Copper, Brass), Very Soft Ferrous Materials	10-4150-010• 0.063in [1.6mm]	10-4250-010• 0.063 in [1.6mm] 102512P* 0.06in [1.5mm]	103012P* 0.079in [2mm]	

AcuThin™ Blades

For certain applications, it is important to minimize the amount of damage done to the sample during sectioning. The AcuThin series offers thin blades that have been developed to minimize the area of cutting thus reducing the amount of damage to the sample. These blades utilize a rubber bond and allow for precise, delicate abrasive sectioning with minimal surface damage. *[Blade Thickness is listed under Part Number]*

Recommended Use	9in [230mm]	10in [254mm]	12in [305mm] Chop	14in [356mm] Chop
General Use <HRC45	102301 0.032in [0.8mm]	102501 0.04in [1mm]	10-4360-010 0.032in [0.8mm]	10-3501 0.063in [1.6mm]
Ferrous Materials >HRC45	10-4161-010 0.025in [0.635mm]	10-4261-010 0.025in [0.635mm]	10-4361-010 0.025in [0.635mm]	103502 0.105in [2.7mm]

Abrasive Blades Selection, 1.25in [32mm] Arbor (Qty 10)

[Blade Thickness is listed under Part Number] ***Rubber Bond*** **= •** ***Resin Bond*** **= ***

Recommended Use	14in [356mm] Chop/Linear	14in [356mm] Orbital	16in [406mm] Orbital	18in [455mm] Orbital
Superalloys, General Steel, Non-Ferrous	12-4305-010• 0.063in [1.6mm]	12-4305-010• 0.063in [1.6mm]	12-5605-010• 0.075in [1.9mm]	12-5805-010• 0.1in [2.5mm]
Ferrous materials >HRC60	10-4310-010• 0.075in [1.9mm] 103509P* 0.098in [2.5mm]	12-4310-010• 0.105in [2.7mm]	12-5610-010• 0.125in [3mm]	12-5810-010• 0.153in [3.8mm]
Ferrous materials HRC50-60	10-4312-010• 0.115in [2.9mm] 103509P* 0.098in [2.5mm]	12-4310-010• 0.105in [2.7mm]	12-5612-010• 0.125in [3mm]	12-5816-010• 0.153in [3.8mm]
Ferrous materials HRC35-50	12-4305-010• 0.063in [1.6mm] 103510P* 0.098in [2.5mm]	12-4316-010• 0.105in [2.7mm]	12-5616-010• 0.125in [3mm]	12-5816-010• 0.153in [3.8mm]
Ferrous materials HRC15-35	12-4305-010• 0.063in [1.6mm] 103511P* 0.098in [2.5mm]	12-4320-010• 0.105in [2.7mm]	12-5616-010• 0.125in [3mm]	12-5816-010• 0.153in [3.8mm]
High Speed Steel, Stainless Steel, Carburized Steel	103508P* 0.098in [2.5mm]			
Delicate Cutting				
Titanium Alloys, Zirconium Alloys, Ductile Materials	10-4345-010• 0.075in [1.9mm] 103507P* 0.098in [2.5mm]		12-5645-010• 0.075in [1.9mm]	12-5845-010• 0.1in [2.5mm]
Non-Ferrous Materials (Aluminum, Copper, Brass), Very Soft Ferrous Materials	10-4350-010• 0.105in [2.7mm] 103512P* 0.098in [2.5mm]			

See Blade Guide for More Information